

Comment on “Two-spinon and four-spinon continuum in a frustrated ferromagnetic spin-1/2 chain”

Recently Enderle *et al.* reported an inelastic neutron scattering (INS) study of the dynamic spin susceptibility $\text{Im}\chi(\omega, k)$ for LiCuVO_4 [1]. Therein they claim that (i) LiCuVO_4 is well described by two interpenetrating, *weakly* ferromagnetically (FM) coupled Heisenberg antiferromagnetic spin-1/2 chains (HAF), (ii) the obtained exchange integrals J_i (NN and NNN inchain couplings $J_1 = -1.6$ meV, $J_2 = 3.56$ meV, diagonal interchain coupling $J_5 = -0.4$ meV in the (ab)-plane, $\alpha = -J_2/J_1 \sim 2.2$) agree with those from an analysis based on spin-wave theory (SWT) [2], (iii) the *observed* INS intensity above 10 meV belongs to a 4-spinon continuum (4SC). Applying exact diagonalization (ED) and DMRG methods to fit INS and magnetization $M(H)$ data, supported by independent microscopic methods [3], we will show that the claims of Ref. [1] are not justified and that LiCuVO_4 exhibits $\alpha < 1$, i.e. *strong* coupling of the HAF, at odds with (i). For possible spin nematics and Bose condensation of 2-magnon bound states in LiCuVO_4 [4, 5] precise knowledge of the coupling regime is of key importance.

Starting from a 2D model, the authors suggest an effective 1D-model with $J_{\text{eff},1} = J_1 + 2J_5 = -2.4$ meV and a renormalized $J_{\text{eff},2} = 2J_2/\pi$, i.e. $\alpha \approx 1.4$. But the applied perturbative method is designed for $\alpha \gg 1$. Further problems occur for the dispersion of spin excitations $\omega(k)$ (dark red curve in Fig. 2 of Ref. 1). Near $k = \pi/4$ the local maximum Ω gives 4.84 meV. For $\alpha = 1.42$ and $J_{\text{eff},1} = -2.4$ meV one has $\Omega = 4.36$ (4.79) meV, only, according to our dynamical DMRG (ED) calculation with $L = 96$ (28) sites of $\text{Im}\chi(\omega, q)$. Fitting our DMRG results for $0.5 \leq \alpha \leq 2$, the general constraint for $\Omega(\alpha)$ reads:

$$4.84 \text{ meV} = \Omega = J_{\text{eff},1} (0.573 - 1.702\alpha + 0.0109\alpha^2). \quad (1)$$

More strikingly, fitting the $M(H)$ -data at $T = 1.6$ K [2, 6] by our DMRG ($T = 0$, $L = 512$ sites), we found $\alpha = 0.75$ (see Fig. 1a). We obtain $H_s = 41.6$ T, $g = 2.27$ and in accord with Ref. 5 $dM/dH_s \approx 0.39$ at low H , where $H_s(M_s)$ is the saturation field (magnetization). Then, Eq. (1) gives $J_{\text{eff},1} = -6.95$ meV and $J_{\text{eff},2} = 5.2$ meV. The 1D-set of Ref. 1 yields a too small $H_s = 37.3$ T at $g = 2.27$ or a too small $g = 2.03$ for $H_s = 41.6$ T, only, and clearly too high M above $0.6H_s$ (see Fig. 1a). If the SWT-fit is meaningful, J_1 is strongly renormalized but $J_{\text{eff},2}$ is close to its bare value of 5.6 meV [2] both at odds with Refs. 1, 2.

With our fitted $J_{\text{eff},2}$ -value, almost the whole region ascribed to the 4SC [1] is covered now by the extended 2-spinon continuum (2SC). The 4SC should be looked for at $k = 0.5$ above 16.3 meV (see Fig. 1c) i.e. in a region which has *not* been measured yet. Since most of the INS intensity below 16 meV belongs to the 2SC, the size of the 4SC enhancement compared to that of a HAF is not yet settled and the 4SC in Fig. 4 of Ref. 1 is overestimated. Figs. 1b, 1c show that the dispersion of the INS peaks is

insufficient to find a unique J_1 - J_2 set. INS intensities or other quantities like $M(H)$ must be analyzed, too. Our set explains the larger INS intensity above 9.5 meV as compared with that in Ref. 1 (see the boxes in Fig. 1).

To conclude, a weakly coupled HAF model with small $|J_1| \leq 5$ meV as in Ref. 1 is not justified for LiCuVO_4 whereas a strong coupling regime with $|J_1| > J_2$ where both J 's exceed significantly those of Ref. 1 is consistent with the INS, the magnetization, and realistic microscopic models of edge-shared cuprates [3]. For strongly coupled HAF's, the 2SC is extended to higher ω with less spectral weight left for the 4SC. Future studies are highly desired to refine the main J 's and the 4SC as well.

S.-L. Drechsler¹, S. Nishimoto¹, R. Kuzian¹, J. Málek^{1,2}, W. Lorenz¹, J. Richter³, J. v. d. Brink¹, M. Schmitt⁴, H. Rosner⁴

¹ Inst. f. Festkörper- u. Werkstoffforschung IFW-Dresden 01171 Dresden, Germany, email: drechsler@ifw-dresden.de

² Institute of Physics, ASCR, Prague, Czech Republic

³ Inst. f. Theor. Physik, Universität Magdeburg, Germany.

⁴ MPI-CPfS Dresden, Germany.

- [1] M. Enderle *et al.*, Phys. Rev. Lett. **104**, 237207 (2010).
- [2] M. Enderle *et al.*, Europhys. Lett. **70**, 237 (2005).
- [3] A strong coupling regime with $\alpha < 1$ is also supported by independent microscopic calculations that predict $J_1 = -6.3$ meV, $J_2 = 5.1$ meV, $\alpha = 0.8$ (mapping a 5-band Hubbard model) and $J_1 = -8.8$ meV, $J_2 = 6.5$ meV, $\alpha = 0.74$ (LSDA+ U). Both methods as our phenomenological analysis given above are valid irrespective of the value of α and have been applied successfully for many related systems. Note that in all systems with a Cu-O-Cu bond angle $\lesssim 95^\circ$ we found a FM NN coupling and $|J_1| \gg 1.6$ meV [7].
- [4] M. Zhitomirsky and H. Tsunetsugu, arXiv:1003.4096v1.
- [5] L.E. Svistov *et al.*, arXiv: 1005.5668v2.
- [6] S.-L. Drechsler *et al.*, J. Mag. & Mag. Mat. **316**, 306 (2007); M. Banks *et al.* J. Phys.: C. M. **19**, 145227 (2007).




FIG. 1. Magnetization of LiCuVO_4 for the 1D J -set of Ref. 1 and our fit compared with experiment ($H \parallel c$) (a). $\text{Im}\chi(\omega, k)$ from exact diagonalizations for both sets for a chain with $L = 28$ sites broadened with 0.05 meV. Red curves: dispersion of spin excitations from main INS peaks [2](b,c). Notice a slight downshift near $k = \pi/4$ of 0.426 meV and 0.676 meV for Fig. 1b(1c), respectively, within the DMRG (see Eq. (1)).

- [7] S.-L. Drechsler *et al.* arXiv:1006:5070 and Refs. therein.